

## Chemical Resistance of Coatings

The following coatings have been tested to be resistant to the chemicals indicated. All coatings must be fully cured (7 days @ 70 +/- 5 °F and 60 +/- 10% RH). ISO groups according to EN 13529:2003.

ISO	CHEMICAL NAME	600	610	620	630	640	650	651	652	670
1	Gasoline	◆	◆	◆	◆	◆	◆	◆	●	◆
2	100LL / Jet-A	◆	◆	◆	◆	◆	◆	◆	●	◆
3	Diesel	◆	◆	◆		◆	◆	◆	●	◆
	Heating Oil	◆	◆	◆		◆	◆	◆	●	◆
4	Motor Oil	◆	◆	◆	◆	◆	◆	◆	●	◆
	Hydraulic Oil	◆	◆	◆	◆	◆	◆	◆	●	◆
	Transmission Fluid	◆	◆	◆	◆	◆	◆	◆	●	◆
	Hydrocarbons	◆	◆				◆	◆	●	◆
	Toluene	◆	◆	◆	◆	◆	◆	◆	●	◆
	Xylene	◆	◆	◆	◆	◆	◆	◆	●	◆
4a	Benzene	◆	◆	◆				◆	●	◆
	Methylnaphthalene	◆	◆	◆				◆	●	◆
4b	Crude Oil	◆	◆	◆	◆			◆	●	◆
5	Mono- / Polyalcohol							◆	◆	◆
5a	Glycol Ether							◆	◆	◆
6	Organic Ester / Ketone							◆		◆
6a	Aromatic Ester / Ketone							◆		◆
7	Aliphatic Aldehyde	◆	◆	◆		◆	◆	◆	◆	◆
	Formaldehyde 40%	◆	◆	◆		◆	◆	◆	◆	◆
8	Organic acids < 10%					◆	◆	◆	◆	
	Acetic Acid					◆	◆	◆	◆	
8a	Organic Acids > 10%							◆		
	Propionic Acid							◆		
9	Inorganic Acids < 20%	◆	◆	◆		◆	◆	◆	◆	◆
	Sulfuric Acid	◆	◆	◆		◆	◆	◆	◆	◆
10	Inorganic Alkali	◆	◆	◆	◆	◆	◆	◆	◆	◆
	Sodiumhydroxide 20%	◆	◆	◆	◆	◆	◆	◆	◆	◆
11	Inorganic Salt Solution	◆	◆	◆	◆	◆	◆	◆	◆	◆
	Sodiumchloride 20%	◆	◆	◆	◆	◆	◆	◆	◆	◆
12	Organic Tensides	◆	◆	◆	◆	◆	◆	◆	◆	◆
13	Non-cyclic Ether							◆		◆
	Diethyl Ether							◆		◆

- ◆ Resistant up to 7 days
- Resistant up to 24 hours
- Blank Not resistant, will discolor or soften